

National Technical Systems

7447 W. 33rd St. N.
Wichita, KS 67205 U.S.A.
Phone: (316) 832-1600
Email: ustl@nts.com

www.nts.com/locations/wichita

HARD ARMOR STAND-ALONE PLATE:

P-BFS TEST

Date Received: December 7, 2022
Via: FedEx
Returned Via: FedEx

Record No.: EXT22002-1
Test Date: December 12, 2022
Customer: Extant Armor Co.

Test Conditions

Temperature: 69.3 °F
Humidity: 52 %

Clay Block No.: 7
Clay Block Size: 24" x 24" x 5.5"
Clay Temperature: 97.7 °F
Drop Average: 20.29 mm

Range 3

Muzzle to Screen 1: 39.30 ft.
Screen 1 - 4: 5.00 ft.
Screen 4 - Target: 5.70 ft.
Midpoint to Target: 8.20 ft.
Barrel Length: 26 in.

Test Standard: IAW Modified / Abbreviated NIJ 0101.06, July 2008
Threat Level: IV

Conditioning: No
Drop Test: No
Submersion: No

Sample Description		Shot / Projectile Description				Chronograph		Test Results	
		Shot No.	Shot Location	Degree Obliquity	Caliber	Bullet Weight (gr.) / Type	TIME sx-5	VELOCITY ft/s	Perforation BFS (mm)
Manufacturer:	Extant Armor Co.	1	Crown	0°	.30 Cal. (.30-06)	166 / M2AP	175.3	2852	43.13
Model No.:	AUXILIA	2	Bottom Left	0°			174.3	2869	40.79
Serial No.:	IV A								
Size (in.):	10 x 12								
Weight (lbs.):	6.804								

This test was performed in accordance with the specification requirements listed in addition to any customer testing modifications or requests. The test results properly reflect the ballistic performance of the listed sample. This test report shall not be reproduced except in full without written approval of National Technical Systems.

Notes:

•Stand-Alone plate tested non-planar (with clay mound / build-up).

Sample Description:

•Customer Proprietary.

Project Manager: Nold
Range Tech(s): Randolph / Zerger